
DENSOLEN®-AS40 Plus/-R20 HT

Product information





Special advantages:



For temperatures up to +85°C (+185°F).



Real co-extruded three-ply tape as the inner layer and two-layer tape as the outer layer.



Fulfills the requirements of EN 12068-C50, DIN 30672-C50 and ISO 21809-3; Type 12A-1.



Excellent mechanical protection and excellent corrosion prevention.



Compatible with factory coatings made of PE, PP, FBE, PU, CTE and bitumen.

Two-tape system for the corrosion prevention coating of metal pipes and pipelines in accordance with DIN 30672 and EN 12068.

For a century now, DENSO Group Germany has been representing experience, quality and reliability for corrosion prevention and sealing technology. The success of the internationally leading corporation is based on the development of the "DENSO-Tape", which was already patented in 1927 as the first product worldwide for the passive corrosion prevention of pipelines. Since then, the DENSO Group Germany has been establishing and guaranteeing the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees continuously implement safe and individual solutions in a personal cooperation with the customer.

Description

DENSOLEN®-AS40 Plus/-R20 HT is a cold applied two-tape system for the corrosion prevention of metal pipes and pipelines in extreme corrosion conditions and mechanical stresses. Compared to the single tape system **DENSOLEN®-AS40 Plus**, a robust and UV resistant surface of the encasement is achieved with the outside tape **DENSOLEN®-R20 HT**.

DENSOLEN®-AS40 Plus/-R20 HT provides a self-amalgamation of the tapes in the overlapping area, which means that a tight and durable hosetype encasement is established.

DENSOLEN®-AS40 Plus/-R20 HT is basically impermeable for water vapor and oxygen and it is resistant against soil bacteria and electrolytes. DENSOLEN®-AS40 Plus/-R20 HT is compatible with factory coatings made of PE, PP, FBE, PU, CTE and Bitumen.

The system **DENSOLEN®-AS40 Plus/** -R20 HT consists of:

DENSOLEN®-HT Primer

A solvent containing primer in accordance with EN 12068 and DIN 30672 for the corrosion prevention with **DENSOLEN®** tapes.


DENSOLEN®-AS40 Plus

A real co-extruded 3-ply plastic tape made from stabilized polyethylene carrier with butyl rubber adhesive on both sides.

DENSOLEN®-R20 HT

A real co-extruded two-ply plastic tape made from stabilized polyethylene carrier film with a butyl rubber adhesive on one side.

The outstanding connection between the adhesive and the carrier film is guaranteed by the co-extruded intermediate layer. The adhesive layer grows completely together with the outside layer of **DENSOLEN®-**AS40 Plus.







Typical product properties

Property		Unit	DENSOLEN®-AS40 Plus Typical value DENSOLEN®-R20 HT Typical value		Test method	
Carrier film color		-	Black, yellow or blue	White, black or blue	-	
Butyl adhesive color inside		-	Grey	Black	-	
Butyl adhesive color outside		-	Black	-	-	
Tape thickness		mm	≥0.8	≥0.5		
Carrier film thickness app.		mm	≥0.28	≥0.3	ISO 4591	
Inside adhesive layer thickness app.		mm	≥0.44	≥0.2	ASTM D1000	
Outside adhesive layer thickness app.		mm	≥0.08	-		
Elongation at break		%	≥600	≥500	DIN 30672	
Tape strength	+23°C (+73°F)	N / cm	≥100	≥65	EN 12068	
Dielectric strength		kV / mm	≥40	≥35	DIN 53481	
Water absorption	+23°C (+73°F) 1 day / 30 days	%	≤0.1 / ≤0.4	≤ 0.1 / ≤0.4	DIN 53495 ASTM D570	

DENSOLEN®-AS40 Plus/-R20 HT with DENSOLEN®-HT Primer

Property	Unit	DENSOLEN®-AS40 Plus/R20 HT Typical value		Require	Test method		
Specific electrical insulation resistance Ohm		≥10 ¹⁰		≥10 ⁸		EN 12068	
Volume resistivity	Ohm cm	≥10 ¹⁵		Not stated		DIN 53482 ASTM D257	
Peel resistance		+23°C (+73°F)	+50°C (+122°F)	+23°C(+73°F)	+50°C(+122°F)		
	N / cm	≥25	≥3	≥10	≥1	EN 12068	
metal/primer/tape		≥45	≥5	Not stated		ASTM D1000	
Peel strength layer to layer	N / cm	+23°C (+73°F)	+50°C (+122°F)				
AS40 PLUS / AS40 PLUS		≥30	≥4	≥10	≥2	EN 12068	
AS40 PLUS / R20 HT		≥30	≥3	≥2	≥2		
R20 HT / R20 HT		≥3	≥3	≥2	≥2		
Indentation resistance - residual layer		+50°C (+122°F)					
thickness at stamp load 10 N/mm² (stamp-Ø 1.8 mm)	mm	≥1.1		≥0.6		EN 12068	
Impact resistance	resistance J ≥16		16	≥15		EN 12068	
Cathodic disbondment resistance	mm	<6		<20		EN 12068	
Lap shear strength	N / cm ²	+23°C (+73°F)					
on steel		≥15		5		EN 12068	
on factory coating	1	≥15		5			

DENSOLEN® tapes can be easily applied manually. The processing with the original **DENSOMAT®** wrapping devices is even more efficient. For **DENSOLEN®** tapes with widths of > 50 mm, we recommend the use of the **DENSOMAT®** wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

			Tape length [m]	Tape area per roll (m²)	Content per box			
		Width [mm]			Number of rolls		Total tape length (m)	App. weight (kg)
DENSOLEN [®] -AS40 Plus	Core Ø 41 mm	30	15	0.45	16	8	270	7.0
		50	15	0.75	12	9	180	9.0
		100	15	1.5	6	9	90	10.2
	Core Ø 78 mm	100	70	7	3	21	210	19.0
		150	70	10.5	2	21	140	19.0
DENSOLEN®-R20 HT	Core Ø 41 mm	50	30	1.5	12	18	360	11.0
		100	30	3.0	6	18	180	11.0
	Core Ø 78 mm	100	70	7	3	21	210	13.0
		150	70	10.5	2	21	140	13.0

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **DENSOLEN®-AS40 Plus/-R20 HT** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Felderstrasse 24 | 51371 Leverkusen | Germany Phone: +49 214 2602-0 | info@denso-group.com

Store in a dry location and do not rest anything against the front of the product.

www.denso-group.com